



Jin Ming Jian De Steel

1.4541

Werkstoff f-Nr	AISI	DIN / DIN EN	UNS	SS	AFN OR	BS	PN
1.454 1	T P 3 2 1	X6 CrNiTi 18-10	S 3210 0	233 7	Z 6 CNT 18.10	32 1 S 31	1H18N 9T

Chemische Analyse nahtloser rohre

C≤%	Si≤%	Mn≤%	P≤%	S%	N%	Cr%	Ni %	Ti%
0,08	1,0	2,0	0,04	0,015 ¹⁾	-	17,0- 19,0	9,0- 12,0 ²⁾	5 x C - 0,7

Mechanische Eigenschaften von Stäben bei Raumtemperatur

Dicke mm _{max}	0,2% Deh _R p _{0,2} N/mm ² _{min}	1,0% Deh _R p _{1,0} N/mm ² _{min}	Zugfestig- keit R _m N/mm ²	Bruchdehnung A ¹⁾ % min (längs)		A ¹⁾ % min (quer)		Kerbschlagarbeit (ISO-V) Raumtemperatur 10mm Dicke J _{min} (längs)	J _{min} (quer)
60	180 ²⁾	215 ²⁾	460-680 ²⁾	35		30		100	60

Tel: 86051088992105 or 8618061535028

Email: info@jmdss.com

Office Address: 2102-2105, Yuexing Building, Guangyi Road, Liangxi District, Wuxi, Jiangsu, China

Factory Address: Metal Materials Market #7, Dongbei Tang District Xishan, Wuxi, Jiangsu, CN

Linkedin: <https://www.linkedin.com/company/jmjdsteel/>

Youtube: <https://www.youtube.com/channel/>

Facebook: <https://www.facebook.com/SSteelfactory>

Tiktok: <https://www.tiktok.com/@jmjd.steelfactory>

Instagram: <https://www.instagram.com/jmjd.steelfactory/>

Pinterest: <https://www.pinterest.com/JMJDWXSteelFactory/>