



Jin Ming Jian De Steel

1.4845

Werkstoff f-Nr .	AISI	DIN / DIN EN	UNS	SS	AFNO R	BS	Pn
1.484 5	TP 31 0 S	X8CrNi2 5-21	S 3100 8	236 1	Z 12 CN 25.20	31 0 S 24	H23N1 8

Chemische Analyse

C≤%	Si≤%	Mn≤%	P≤%	S≤%	N%	Cr%	Ni%
0,15	0,75	2,0	0,045	0,03	-	24,0- 26,0	19,0- 22,0

Zunderbestandigkeit in luft:

1.050° C

Tel: 860510 8899 2105 or 86 1 8 0 6 1 5 3 5 0 2 8

Email: info@jmidss.com

Office Address: 2102-2105, Yuexing Building, Guangyi Road, Liangxi District, Wuxi, Jiangsu, China

Factory Address: Metal Materials Market #7, Dongbei Tang District Xishan, Wuxi, Jiangsu, CN

Linkedin: <https://www.linkedin.com/company/jmjdsteel/>

Youtube: <https://www.youtube.com/channel/>

Facebook: <https://www.facebook.com/SSteelfactory>

Tiktok: <https://www.tiktok.com/@jmjd.steelfactory>

Instagram: <https://www.instagram.com/jmjd.steelfactory/>

Pinterest: <https://www.pinterest.com/JMJDWXSteelFactory/>