



Jin Ming Jian De Steel

1.40404

Werkstoff- Nr	AISI	DIN / DIN EN	UNS	SS	AFNOR	BS	PN
1.4404	TP 316 L	X2CrNiMo17-12-2	S 316 03	234 8	Z 3 CND 18.12.0 2	316 S11	00H17N14M2

Chemische Analyse nahtloser Rohre

C ≤ %	Si ≤ %	Mn ≤ %	P ≤ %	S ≤ %	N ≤ %	Cr %	Mo %	Ni %
0,03	1,0	2,0	0,04	0,015 ¹⁾	0,11	16,5-18,5	2,0-2,5	10,0-13,0 ²⁾

Mechanische Eigenschaften nahtloser Rohre bei Raumtemperatur

Dicke mm _{max}	Dehngrenze $R_{p0,2}$ 0,2% $R_{p1,0}$ 1,0% N/mm ² _{min}		Zugfestigkeit R_m N/mm ²	Bruchdehnung A ₁₎ % _{min} (längs) A ₁₎ % _{min} (quer)		Kerbschlagarbeit (ISO- V) Raumtemperatur ≥ 10mm Dicke J _{min} (längs) J _{min} (quer)	
60	190 ²⁾	225 ²⁾	490-690 ³⁾	40	30	100	60

Tel: 86051088992105 or 8618061535028

Email: info@jmdss.com

Office Address: 2102-2105, Yuexing Building, Guangyi Road, Liangxi District, Wuxi, Jiangsu, China

Factory Address: Metal Materials Market #7, Dongbei Tang District Xishan, Wuxi, Jiangsu, CN

Linkedin: <https://www.linkedin.com/company/jmjdsteel/>

Youtube: <https://www.youtube.com/channel/>

Facebook: <https://www.facebook.com/SSteelfactory>

Tiktok: <https://www.tiktok.com/@jmjd.steelfactory>

Instagram: <https://www.instagram.com/jmjd.steelfactory/>

Pinterest: <https://www.pinterest.com/JMJDWXSteelFactory/>