



# Jin Ming Jian De Steel

## 1.4876

Werkstoff-Nr	AISI	DIN / DIN EN	UNS	SS	AFNOR	BS
1.4876	Alloy 800	X10NiCrAlTi3220		-	Z 8 NC 32.21	3076 NA 15 H

## Chemische Analyse

C≤%	Si≤%	Mn≤%	P≤%	S≤%	Al%	Ti%	Cr%	N
0,12	1,0	2,0	0,03	0,02	0,15-0,6	0,15-0,6	19,0-23,0	30,0-34,0

## Zunderbeständigkeit in luft:

1.100° C

Tel: 86051088992105or8618061535028

Email: [info@jmqdss.com](mailto:info@jmqdss.com)

OfficeAddress: 2102-2105, YuexingBuilding, GuangyiRoad, LiangxiDistrict, Wuxi, Jiangsu, China

actoryAddress: [Metal Materials Market #7](#), Dongbei Tang District Xishan, Wuxi, Jiangsu, CN

Linkedin: <https://www.linkedin.com/company/jmqdsteel/>

Youtube: <https://www.youtube.com/channel/>

Facebook: <https://www.facebook.com/SSteelFactory>

Tiktok: <https://www.tiktok.com/@jmqd.steelFactory>

Instagram: <https://www.instagram.com/jmqd.steelFactory/>

Pinterest: <https://www.pinterest.com/JMQDWXSteelFactory/>