



Jin Ming Jian De Steel

1.4876

Werkstoff-Nr	AISI	DIN / DIN EN	UNS	SS	AFNOR	BS
1.4876	Alloy 800	X10NiCrAlTi3220	-	-	Z 8 NC 32.21	3076 NA 15 H

Chemische Analyse

C≤%	Si≤%	Mn≤%	P≤%	S≤%	Al%	Ti%	Cr%	N
0,12	1,0	2,0	0,03	0,02	0,15-0,6	0,15-0,6	19,0-23,0	30,0-34,0

Zunderbeständigkeit in luft:

1.100° C

Tel: 86 0510 8899 2105 or 86 189 6174 6817

Email: sales01@wxjmdss.com

Linkedin: <https://www.linkedin.com/company/jmjdsteel/>

Youtube: https://www.youtube.com/channel/UCsH_EaPATsBQsMMhoV7C33w

Facebook: <https://www.facebook.com/SSteelfactory>

Office Address: 2102-2105, Yuexing Building, Guangyi Road, Liangxi District, Wuxi, Jiangsu, China

Factory Address: Metal Materials Market #7, Dongbei Tang District Xishan, Wuxi, Jiangsu, CN